

Grout T

Thixotropic Grout Mortar

Product Description:

This is a mineral and cement-based, flexible, fast drying, thixotrope grout mortar that is prepared with reinforcement of cement and high quality chemical additives. It is used in the tasks of fastening various elements such as steel construction, equipments and machine foundations both interior and exterior. It has a very strong adhesion feature with high first and second compressive strengths.

Areas of applications:

- Interior and exterior
- In concrete fastening and tasks of reinforced concrete
- In multi-purpose moulded anchorage tasks
- In crane rails and piers
- In the joints of roads and bridges

Features:

- Thixotrope feature. It won't cause slipping and sagging vertically.
- Long applicability period
- For concreting the joints of steel elements and concrete elements
- For making all kind of anchorage, assembly and concrete repair; and filling piers
- For installing railways, placing lids of sewages and water channels
- For fastening bridge parapets, traffic lights, billboards to the floor and fastening the reinforcements while enhancing girder-columns
- High first and second compressive strengths
- Adheres to steel very strongly, absorbs the tension
- Resistant to water, constant wetness, frost and heavy weather conditions
- No shrinkage
- Fireproof, therefore it is used safely in the areas where epoxy use is risky

Technical data:

Dmax (mm)	2
Colour	Grey
Applicable Thickness (mm)	30
Dry Unit Volume Weight (kg / lt)	1,6 ± 0,2
Wet Unit Volume Weight (kg / lt)	2,2 ± 0,2
Drying Time in Container (min)	~ 60
Drying Time (hour)	~ 24
Compressive Strength (28 days) (N/mm ²)	≥ 60
Bending Strength (28 days) (N/mm ²)	≥ 6
Expansion ratio	0,2 %
Mixture water amount (for 25 kg dry mortar)	3,5 - 4 lt
Environment temperature for application	Between +5°C and +35°C

Technical data are approximately provided according to a temperature of + 20°C and a relative humidity of 50%.

Preparing the substrate :

- The application surface should be dry, clean and free from dirt and other adherence reducing materials as well as crack-free, stable and strong enough to bear burden.
- When necessary, application surface should be cleaned with sanding, pressure water or pressure air spraying method. Before the anchorage, the surface should be wetted sufficiently, however water accumulation on the surface should be avoided.

Application:

- Water (2/3 of the amount stated on the chart above) at normal environment temperature is poured into a clean container. Then, some dry mortar is added in the container which is full of water and mixed with a

suitable mixing machine or device without stopping. It is mixed until a smooth and homogenous mixture is obtained.

- Some amount of water, which should not exceed the amount stated on the technical data chart, can be added in the mortar prepared in order to obtain the desired consistency.
- After 2 minutes' aging period, the mortar is mixed gently again. The mortar, which is now ready to apply and highly fluid, should be applied within maximum one hour.
- In order to prevent air bubble formation in the mortar, or if an anchorage is to be carried out without mould, the application should start from only one corner or edge, and the air inside should be released. The poured mortar should be mixed and checked with a tool when necessary and air bubbles should be removed.

After application:

The exposed and newly applied surfaces should be protected against fast drying for minimum 3 days. To avoid it, keeping the surface humid by using wide folios and humid jute sacks would be enough.

Coverage:

Approx. 18 – 22 kg/m² for 10 mm thickness.

The coverage amounts are theoretical and it is recommended to do coverage-controlled sample application before treatment.

Packaging:

In 25 kg craft bags, 64 bags in 1 palette (1600 kg/palette)

Storage:

- Dry mortar bags should be protected from water, frost and adverse air conditions.
- They should be kept dry and cool on wooden palettes.
- The torn and opened drums should be closed immediately and consumed first.
- Maximum 8 bags are stacked on each other.
- Shelf life is maximum 12 months conditional to complying with the abovementioned storage conditions.

Risk Signs :

R23/24/25 : Poisonous when inhaled, swallowed and contacted with skin.

Security signs:

S2: Keep out of reach of children.

S3: Keep cool.

S9: Keep the package dry.

S26: Rinse with water thoroughly when contacted with eyes and consult a doctor.

S28: Rinse with water thoroughly when contacted with skin and consult a doctor.

S29: Do not throw in the drain.

S36/37/39: Wear suitable protective clothing, protective gloves and glasses / mask during the operation.

BOSTIK is only responsible for the product quality and cannot be held responsible for its mis-use except for the recommendations regarding where and/or how the product shall be used. This technical bulletin hereby is valid until it is renewed. BOSTIK's right to amend the products in accordance with technical developments is reserved.



Akçaburgaz Mh. ALKOP Sit. 1575 Sk. C2 Blok No.5-14 Esenyurt 34555 İstanbul
Tel. (+90 212) 858 01 26 Fax. (+90 212) 858 01 34
info@bostik.com.tr - www.bostik.com.tr